



TECHNICAL DATA SHEET (TDS)

LLDPE LL1-18B LINEAR LOW DENSITY POLYETHYLENE

OVERVIEW: Butene copolymer.

Toughness and strength.

Applications: Stretch wrap, blend resin, industrial packaging.

Complies with the specifications U.S FDA 21 CFR 177.1520 (C) 3.2a.

ADDITIVE: Antiblock: No Slip: No Processing Antioxidant: Yes

Properties	Test Method	Units	Nominal Values
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10min	1.0
Density	ASTM D792	g/cm ³	0.918
Film Properties			
Tensile strength at yield MD	ASTM D882	Psi/MPa	1600/11
Tensile strength at yield TD	ASTM D882	Psi/MPa	1600/11
Tensile strength MD	ASTM D882	Psi/MPa	7100/49
Tensile strength TD	ASTM D882	Psi/MPa	4900/34
Elongation MD	ASTM D882	%	540
Elongation TD	ASTM D882	%	830
1% Secant Modulus MD	ASTM D882	Psi/MPa	29000/200
1% Secant Modulus TD	ASTM D882	Psi/MPa	33400/230
Dart Drop Impact (F ₅₀)	ASTM D1709/A	g	100
Haze	ASTM D1003	%	11
Gloss (45°)	ASTM D2457		56

Film properties are typical of blown film extruded on a 2.5' extruder with 4' die and 100-mil die gap at a blow up ratio of 2, 5:1. But are dependent upon operating conditions.

The above information is provided in good faith. PACIFIC is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, PACIFIC MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

825 BRICKELL BAY DRIVE, SUITE 1750, MIAMI, FLORIDA 33131
TELEPHONE (305) 358-1900 WWW.PACIFIC-LTD.COM



Rev. April 2022