



TECHNICAL DATA SHEET (TDS)

LLDPE LL1-24X LINEAR LOW DENSITY POLYETHYLENE

OVERVIEW: Hexene copolymer.

Good toughness and tear resistance.

Complies with: U.S. FDA, FCN 741

ADDITIVE: Antiblock: 2500 ppm Slip:1000 ppm Processing Aid: No

Properties	Test Method	Units	Nominal Values
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10min	1.3
Density	ASTM D792	g/cm ³	0.924
Properties			
Tensile strength at yield MD	ASTM D882	Psi/MPa	1730/11.9
Tensile strength at yield TD	ASTM D882	Psi/MPa	1790/12.4
Tensile strength at break MD	ASTM D882	Psi/MPa	5900/40.7
Tensile strength at Break TD	ASTM D882	Psi/MPa	4660/32.1
Elongation MD	ASTM D882	%	680
Elongation TD	ASTM D882	%	730
2% Secant Modulus MD	ASTM D882	Psi/MPa	26100/180
2% Secant Modulus TD	ASTM D882	Psi/MPa	31700/218
Dart Drop Impact (F₅₀)	ASTM D1709/B	g	170
Haze	ASTM D1003	%	13
Gloss (45°)	ASTM D2457		59
Elmendorf Tear Strength MD	ASTM 01922	g	680
Elmendorf Tear Strength TD	ASTM 01922	g	1100

Film properties are typical of blown film extruded on a 25" extruder with 6" die and 70-mil die gap at a blow up ratio of 2.5:1, but are dependent upon operating conditions

The above information is provided in good faith. PACIFIC is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, PACIFIC MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBE D, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

825 BRICKELL BAY DRIVE, SUITE 1750, MIAMI, FLORIDA 33131
TELEPHONE (305) 358-1900 WWW.PACIFIC-LTD.COM



Rev. April 2022