



TECHNICAL DATA SHEET (TDS)

LLDPE LL2-20-OA LINEAR LOW DENSITY POLYETHYLENE

OVERVIEW: Octene copolymer.

Exceptional toughness, low gel level.

Applications: cast stretch wrap, co-extrusion and lamination.

Complies with the specifications U.S FDA 21 CFR 177.1520 (C) 3.2a.

ADDITIVE: Slip: None Antiblock: None Processing Antioxidant: Yes

Properties	Test Method	Units	Nominal Values
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10min	2.3
Density	ASTM D792	g/cm ³	0.92
Properties			
Tensile strength at yield MD	ASTM D882	Psi/MPa	1300/8.9
Tensile strength at yield TD	ASTM D882	Psi/MPa	1200/8.4
Tensile strength MD	ASTM D882	Psi/MPa	4800/33
Tensile strength TD	ASTM D882	Psi/MPa	3600/25
Elongation MD	ASTM D882	%	435
Elongation TD	ASTM D882	%	760
1% Secant Modulus MD	ASTM D882	Psi/MPa	20300/140
1% Secant Modulus TD	ASTM D882	Psi/MPa	23200/160
Dart Drop Impact (F ₅₀)	ASTM D1709/A	g	190
Haze	ASTM D1003	%	2
Gloss (45°)	ASTM D2457		85

Film properties are typical of cast film extruded at a melt temperature of 500° F, and a line speed of 800 ft./min.

The above information is provided in good faith. PACIFIC is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, PACIFIC MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

825 BRICKELL BAY DRIVE, SUITE 1750, MIAMI, FLORIDA 33131
TELEPHONE (305) 358-1900 WWW.PACIFIC-LTD.COM



Rev. April 2022