



## TECHNICAL DATA SHEET (TDS)

# PP PP35-0H POLYPROPYLENE

**OVERVIEW:** Prime Homopolymer – controlled rheology with excellent processability and gas fade resistance.

Applications: spunbond nonwoven fabric high speed melt spinning applications, multifilament yams, and extrusion coating.

Complies with the specifications U.S. FDA 21 CFR 177.1640.

**ADDITIVE:** none

Properties	Test Method	Units	Nominal Values
Melt Index 230° C/2.16 Kg	ASTM D-1238 Condition "L"	g/10min	35
Density	ASTM D1505	g/cm <sup>3</sup>	0.905

The above information is provided in good faith. PACIFIC is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, PACIFIC MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBE D, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

**825 BRICKELL BAY DRIVE, SUITE 1750, MIAMI, FLORIDA 33131  
TELEPHONE (305) 358-1900 WWW.PACIFIC-LTD.COM**



Rev. April 2022