



## TECHNICAL DATA SHEET (TDS)

# PP PP4-OR POLYPROPYLENE

**OVERVIEW:** Prime Homopolymer with excellent low water carryover.

Application: Raffia.

**ADDITIVE:** None.

Properties	Test Method	Units	Nominal Values
Melt Index Rate, 230 °C /2.16 Kg	ASTM D1238	g/10min	4.0
Density	ASTM D1505	g/cm <sup>3</sup>	0.9
Properties			
Tensile strength at yield (50 mm/min)	ASTM D638	Psi	4800
Elongation yield (50 mm/ min)	ASTM D638	%	9
Flexural Modulus (1.3 mm/min) 1% Secant	ASTM D790	psi	180000
Rockwell Hardness, R Scale	ASTM D785		180000
Notched Izod Impact Strength @ 73° F	ASTM D256	ft-lb/in	0.8

*Values are intended as guides only, not specifications. Specimens were injection molded.*

The above information is provided in good faith. PACIFIC is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, PACIFIC MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBE D, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

**825 BRICKELL BAY DRIVE, SUITE 1750, MIAMI, FLORIDA 33131  
TELEPHONE (305) 358-1900 WWW.PACIFIC-LTD.COM**



Rev. April 2022