



## TECHNICAL DATA SHEET (TDS)

# HDPE HMW9-50 HIGH DENSITY POLYETHYLENE

### OVERVIEW:

Broad molecular weight distribution, excellent tear strength, exceptional impact strength and excellent processability, moderate swell.

Applications t-shirts, bags, trash can lines, merchandise.

Complies with the specifications U.S FDA 21 CFR 177.1520.

### ADDITIVE:

Properties	Test Method	Units	Nominal Values
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10min	0.08
Density	ASTM D792	g/cm <sup>3</sup>	0.951
<b>Properties</b>			
Tensile strength at yield MD	ASTM D882	Psi	5300
Tensile strength at yield TD	ASTM D882	Psi	5000
Tensile strength at break MD	ASTM D882	Psi	9200
Tensile strength at break TD	ASTM D882	Psi	9800
Elongation MD	ASTM D882	%	300-500
Elongation TD	ASTM D882	%	300-500
2% Secant Modulus MD	ASTM D882	Psi/MPa	122000
2% Secant Modulus TD	ASTM D882	Psi/MPa	132000
Dart Drop Impact Strength (F <sub>50</sub> )	ASTM D1709A	g	350

The values were measured on a 20 µm film in a blown film line with 4:1 BUR and 50 mm Alpine extruder.

The above information is provided in good faith. PACIFIC is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, PACIFIC MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBE D, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

**825 BRICKELL BAY DRIVE, SUITE 1750, MIAMI, FLORIDA 33131  
TELEPHONE (305) 358-1900 WWW.PACIFIC-LTD.COM**



Rev. April 2022