



TECHNICAL DATA SHEET (TDS)

HDPE IM40-50 HIGH DENSITY POLYETHYLENE

OVERVIEW: Excellent processability, impact resistance

Applications: food container applications.

Complies with the specifications U.S FDA 21 CFR 177.1520

ADDITIVE: Additives: Antiblock: None Slip: None

Properties	Test Method	Units	Nominal Values
Melt Index	ASTM D1238	g/10 min	40
Density	ASTM D792	G/CC	0.952
Properties			
Tensile strength at Yield	ASTM D638	Psi/MPa	2900/20
Ultimate Tensile	ASTM D638	Psi/MPa	1600/11
Elongation	ASTM D638	%	250
Notched Izod Impact	ASTM D256	@ 50°C,ft.lb/in(J/cm)	0.9/49
Notched Izod Impact @ - 23°C,ft.lb/in	ASTM D256	@ 23°C,ft.lb/in(J/cm)	0.4/21
Flexural Modulus	ASTM D790	Psi/MPa	132000/910
Tensile Modulus, 2% secant	ASTM D790	Psi/MPa	89000/614

Physical properties measured on compression molded specimens

The above information is provided in good faith. PACIFIC is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, PACIFIC MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBE D, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

**825 BRICKELL BAY DRIVE, SUITE 1750, MIAMI, FLORIDA 33131
TELEPHONE (305) 358-1900 WWW.PACIFIC-LTD.COM**



Rev. April 2022