



TECHNICAL DATA SHEET (TDS)

HDPE IM7-54 HIGH DENSITY POLYETHYLENE

OVERVIEW:

Excellent processability, outstanding balance of stiffness, cold temperature impact, toughness and ESCR, good organoleptic properties and color

Applications: Bulk food, industrial and lubricant shipping pails, caps and closures bins and totes.

Complies with the specifications U.S FDA 21 CFR 177.1520

ADDITIVE:

Antioxidant.

Properties	Test Method	Units	Nominal Values
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10 min	6.7
Density	ASTM D792	g/cm ³	0.954
Film Properties			
Tensile strength at yield (50mm/min)	ASTM D638	Psi/MPa	4100/28
Elongation @break (50 mm/min)	ASTM D638	%	1300
Flexural Modulus	F 790	Psi/MPa	155000/1070
Hardness, Shore D	ASTM D2240	—	63
Softening Point (Vicat)	ASTM D1525	°C(°F)	124(255)
ESCR F50	ASTM D1693	H	<10

Physical properties measured on compression molded specimens

The above information is provided in good faith. PACIFIC is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, PACIFIC MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

**825 BRICKELL BAY DRIVE, SUITE 1750, MIAMI, FLORIDA 33131
TELEPHONE (305) 358-1900 WWW.PACIFIC-LTD.COM**



Rev. April 2022