



TECHNICAL DATA SHEET (TDS)

LDPE LD02GP LOW DENSITY POLYETHYLENE

OVERVIEW: Tubular resin, Blown process
Complies with the specifications U.S FDA 21 CFR 177.1520 (C) 3.2 a.

ADDITIVE: Antiblock:1250ppm Slip: 700 ppm

Properties	Test Method	Units	Nominal Values
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10 min	2.0
Density	ASTM D792	g/cc	0.9215
Film Properties			
Tensile strength at yield MD	ASTM D882	Psi/MPa	1790/12
Tensile strength at yield TD	ASTM D882	Psi/MPa	1760/12
Tensile strength at break MD	ASTM D882	Psi/MPa	3597/25
Tensile strength at break TD	ASTM D882	Psi/MPa	3329/23
Elongation MD	ASTM D882	%	417
Elongation TD	ASTM D882	%	665
2% Secant Modulus MD	ASTM D882	Psi/MPa	26187/181
2% Secant Modulus TD	ASTM D882	Psi/MPa	30026/207
Haze	ASTM D1003	%	8.9
Gloss @ 45°	ASTM D2457		66
Dart Drop Impact Strength, F50	ASTM D1709A	g	154
Elmendorf Tear Strength MD/TD	ASTM D1922	g	498/284

The values were measured on a 51 µm film in a blown film line with 2.5:1BUR and 1 mm die gap.

The above information is provided in good faith. PACIFIC is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their uses. Further, PACIFIC MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBED, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR

825 BRICKELL BAY DRIVE, SUITE 1750, MIAMI, FLORIDA 33131
TELEPHONE (305) 358-1900 WWW.PACIFIC-LTD.COM

