



## TECHNICAL DATA SHEET (TDS)

# LDPE LD03GP LOW DENSITY POLYETHYLENE

**OVERVIEW:** Resin for general purpose, optimal gauge: 0.8 – 3.0 mil.

Applications: blown film

Complies with the specifications U.S FDA 21 CFR 177.1520 (c) 2.1

**ADDITIVE:** Antiblock: 1200 ppm      slip: 750 ppm

Properties	Test Method	Units	Nominal Values
Melt Index (190° C/2.16 Kg)	ASTM D1238	g/10 min	3.0
Base Resin Density (23° C)	ASTM D1505	g/cm <sup>3</sup>	0.9225
<b>Film Properties</b>			
Tensile strength at yield MD	ASTM D882	Psi/MPa	1765/12
Tensile strength at yield TD	ASTM D882	Psi/MPa	1764/12
Tensile strength at break MD	ASTM D882	Psi/MPa	3168/22
Tensile strength at break TD	ASTM D882	Psi/MPa	2507/17
Elongation MD	ASTM D882	%	506
Elongation TD	ASTM D882	%	664
Haze	ASTM D1003	%	9.5
Gloss @ 45°	ASTM D2457		68.7
Dart Drop Impact Strength, F50	ASTM D1709	g	94
Elmendorf Tear Strength MD/TD	ASTM D1922	g	498/456

The values were measured on a 51 µm film in a blown film line with 2.5:1BUR and 1.016 mm die gap.

The above information is provided in good faith. PACIFIC is not responsible for any processing or compounding which may occur to produce finished articles, packaging materials or their components. Further, PACIFIC MAKES NO WARRANTY OR REPRESENTATION OF ANY KIND, REGARDING THE INFORMATION GIVEN FOR THE PRODUCTS DESCRIBE D, AND EXPRESSLY DISCLAIMS ALL IMPLIED WARRANTIES, REPRESENTATIONS AND CONDITIONS, INCLUDING WITHOUT LIMITATION ALL WARRANTIES AND CONDITIONS OF QUALITY, MERCHANTABILITY AND SUITABILITY OR FITNESS FOR PARTICULAR PURPOSE.

825 BRICKELL BAY DRIVE, SUITE 1750, MIAMI, FLORIDA 33131  
TELEPHONE (305) 358-1900 WWW.PACIFIC-LTD.COM

